

Neoproof[®] Polyurea L

Description of the product

Neoproof[®] Polyurea L is a 2-component, pure aliphatic, brushable polyurea waterproofing coating for roofs, when mechanical durability and outstanding waterproofing properties are required. It forms a blister-free, non-penetrating against moisture film, providing zero water absorption and remarkably high resistance against UV and mechanical stress.

Applications

- Roofs made of concrete, cement boards, mosaic, cement slurries
- Rooftops with resistance to stagnant water
- Metallic surfaces after the application of the proper primer (use **Neopox[®] Special Primer 1225** in the cases where anticorrosive protection is needed)
- New or old polyurethane waterproofing layers
- Top-coat over fast-setting sprayable aromatic polyurea
- Protection of polyurethane foam insulation

Properties/Advantages

- Prevents moisture penetration, providing complete sealing
- Offers increased resistance to bending and stretching
- Very high mechanical strength
- Remarkable resistance against UV
- Excellent bonding to all building substrates such as concrete, plaster, masonry, metal, wood
- Blister free coating. No appearance of holes in the surface during the curing of material
- Dries and cures quickly
- Long pot life
- Crack bridging properties
- Easy to apply
- Long-lasting waterproofing protection
- Ideal solution for waterproofing walkable roofs
- Resistant to temperatures from -35°C to +80°C

Technical Characteristics

Density (EN ISO 2811-1:2011) 1,40-1,50 kg/l

Solids by weight (ASTM D5201) >85%

The information supplied in this datasheet, concerning the uses and the applications of the product, is based on the experience and knowledge of NEOTEX[®] SA. It is offered as a service to designers and contractors in order to help them find potential solutions. However, as a supplier, NEOTEX[®] SA does not control the actual use of the product and therefore cannot be held responsible for the results of its use. As a result of continual technical evolution, it is up to our clients to check with our technical department that this present data sheet has not been modified by a more recent edition.

Neoproof[®] Polyurea L

Service temperature	-35 ⁰ C min / +80 ⁰ C max
Hardness Shore A (EN ISO 868:2003/ASTM 2240)	78
Hardness Shore D (EN ISO 868:2003/ASTM 2240)	30
Consumption	1-1,2 kg/m ² (for 2 layers, on cementitious substrate)
Absorption Coefficient (EN 1062-3:2008)	0.00 kg/m ² min ^{0,5}
Substrate humidity	<4%
Application temperature	+5 ⁰ C to +35 ⁰ C
Elongation (ASTM D412)	470%
Tensile strength at break (23 ⁰ C)	10.1 N/mm ²
Adhesion to concrete (ASTM D4541)	> 3N/mm ²

Pot life

Temperature	Time
5 °C	140 minutes
23 °C	100 minutes
35 °C	60 minutes

Tack free

Temperature	Time
5 °C	10 hours
23 °C	5 hours
35 °C	3 hours

Neoproof[®] Polyurea L

Recoat / Walkability

Temperature	Time
5 °C	24 hours
23 °C	18 hours
35 °C	12 hours

Instructions for use

Surface preparation: The surfaces should be smooth and continuous (i.e. without holes, cracks, bays, etc.). In the opposite case, they should be treated accordingly (e.g. with puttying). Moreover, they should be clean, dry and free from dust, oils, greases and loose material. Prior to the application, for the filling of the pores, the enhancement of the adhesion and the higher coverage of the material, it is suggested to apply **Acqua[®] Primer NP**, diluted with water (10-15% by weight). The substrate temperature must be higher than +12°C.

Application: Mix the two parts adding Part B to Part A under stirring (400rpm) for 2-3 minutes. **Neoproof[®] Polyurea L** is applied after good stirring with brush, roller, or airless spray, 24 hours after the priming with **Acqua[®] Primer NP**. **Neoproof[®] Polyurea L** is applied in two layers without dilution.

Special Notes

- **Neoproof[®] Polyurea L** should not be applied under wet conditions, or if wet conditions are expected to prevail during the curing period of the product.
- Application conditions: Surface moisture: < 4%, Relative atmosphere moisture: <85%. The application should take place under temperature between +5°C and +35°C.

ATHENS: V. MOIRA, INDUSTRIAL AREA MANDRA, 19600, ATHENS, GREECE, TEL.:+30 210 5557579, FAX: +30 210 5558482


THESSALONIKI: 10th km N.R THESSALONIKIS-POLIGIROU, 57001, THERMI THESSALONIKI, GREECE, TEL.:+30 2310 467275, FAX: 2310 463442

Neoproof[®] Polyurea L

Colours	White
Packaging	Sets of 21 kg in tin cans (components A&B have fixed weight proportion)
Tools cleaning	Use solvent Neotex[®] 1021 immediately after application.
Stain removal	Use solvent Neotex[®] 1021 when the stains are still fresh and damp. In case of hardened stains, use mechanical means.
Storage stability	Part A: 2 years (5-45°C) in sealed tin cans. Part B: 1 year (5-35°C) in sealed tin cans.



Neoproof[®] Polyurea L



1922

NEOTEX S.A.
V. Moira str., P.O. Box 2315
GR 19600 Industrial Area Mandra, Athens, Greece

16

1922-CPR-0386

DoP No. Neoproof Polyurea L / 4950-16

EN 1504-2

Neoproof Polyurea L

Surface protection system for concrete
Coating

Water vapour permeability	:	Class II
Capillary absorption and permeability to water	:	$W < 0,1 \text{ kg/m}^2 \text{ h}^{0,5}$
Adhesion strength	:	$\geq 1,5 \text{ N/mm}^2$
Permeability to CO ₂	:	$s_D > 50 \text{ m}$
Reaction to fire	:	Euroclass F
Dangerous substances	:	comply with 5.3